

TITAN™ SEAMLESS UV RESISTANT RUBBER PIPE INSULATION*



Seamless

*Patent Pending

- Closed cell elastomeric foam NBR/PVC tube with flexible polymeric jacketing material
- Seamless - Non-slit for slide-on applications
- For use on HVAC/R, commercial, and industrial process piping and equipment
- Ideal for outdoor applications: UV resistant, tear resistant, weather resistant
- 1-Step Install: No field applied protective coating or additional jacketing required
- High resistance to moisture vapor intrusion; low thermal conductivity
- CARTON QUANTITIES ONLY

TITAN™ SEAMLESS UV RESISTANT RUBBER PIPE INSULATION ⇄ TECHNICAL DATA				
Physical properties		Titan™ Seamless UV Resistant Rubber Pipe Ins		Test methods
Main Composition		Flame-retarded NBR/PVC elastomeric foam with proprietary copolymer blend jacket		-
Thermal Conductivity (Btu-in/hr-Ft ² -°F)	75°F (24°C) Mean Temp	0.242		ASTM C177
Density		3-6 lb/ft ³		ASTM D1667
Operating Temperature Range		-70°F* (-57°C) to +220°F (+104°C)		ASTM C534
Water Vapor Permeability (Dry Cup)	(Core Material Only)	<0.01 perm-in		ASTM E96
Water Vapor Permeance	(Jacket Material)	≤0.05 perms		ASTM E96
Dimensional Stability		<7% Linear Shrinkage		ASTM C534
Corrosion Risk		pH neutral		DIN 1988
UV Resistance (Artificial Aging)	(Jacket Material)	Pass: No Changes to Surface Condition Excellent – No Deterioration		ASTM G153 ASTM G154 tested to 3,000 hours
Flammability		25/50 (up to 1-1/2") HF-1, V-0, 5VA		ASTM E84 UL 94
Tensile Strength		1,200 psi min.		ASTM D412
Elongation		150% min.		ASTM D412
Hot surface Performance at 250°F (121°C)		pass		ASTM C411 NFPA 90 A

* For applications below -40°F (-40°C), contact us.

TITAN™ SEAMLESS UV RESISTANT RUBBER PIPE INSULATION ⇄ THICKNESS RECOMMENDATIONS - TO PREVENT CONDENSATION			
SERVICE TEMPERATURE	-20°F (-29°C)	50°F (10°C)	
3/8" ID to 1-1/2" ID	1"	1/2"	
1-1/2" IPS to 2-7/8" IPS	1"	1/2"	

Thickness listed for the specified ranges will prevent condensation on indoor piping under the defined design conditions. Normal: 85°F and 70% R.H.

TITAN™ SEAMLESS UV RESISTANT RUBBER PIPE INSULATION ⇄ FOR ENERGY CONSERVATION (ASHRAE 90.1 - 2010)				
NOMINAL PIPE OR TUBE SIZE, INCHES	< 40°F < 4.4°C	40-60 °F 4.4-15.6°C	105-140 °F 40.6-60 °C	141-200°F 60.6-93.3°C
< 1"	0.5	0.5	1.0	1.5
1" to 1 1/2"	1.0	0.5	1.0	1.5
1 1/2" to 4"	1.0	1.0	1.5	2.0

TITAN™ SEAMLESS UV RESISTANT RUBBER PIPE INSULATION ⇄ PIPE "R" VALUES PER SQUARE FOOT (ALL SIZES ARE NOMINAL)					
Nominal insulation I.D.	1/2" WALL	3/4" WALL	1" WALL	1-1/2" WALL	
1/4"	4.0	6.1	9.6	16.5	
3/8"	3.6	5.6	8.5	14.6	
1/2"	3.4	5.4	7.9	13.5	
5/8"	3.3	5.4	7.5	12.8	
3/4"	3.1	5.4	7.5	12.4	
7/8"	3.2	5.4	7.2	11.6	
1-1/8"	3.1	5.5	7.1	10.8	
1-3/8"	3.2	5.3	7.3	-	
1-5/8"	3.1	5.1	7.1	-	
1-1/2" IPS	2.6	4.4	6.2	-	
2-1/8"	3.0	4.9	6.6	-	
2" IPS	2.9	4.8	-	-	
2-1/2" IPS	3.0	-	-	-	
2-5/8"	3.1	-	-	-	

- ### SPECIFICATION COMPLIANCE
- ▶ 2012 IECC Section R403.3.1 (residential) Section C403.2.8 (commercial)
 - ▶ 2015 and 2018 IECC Section R403.4.1 (residential) Section C403.2.10.1 (commercial)
 - ▶ 2012, 2015 and 2018 IRC Section N1103.4.1
 - ▶ 2016 California Energy Code, Part 6 Subchapter 3, Section 120.3
 - ▶ ASTM E84 25/50-rated (to 1-1/2") CAN/ULC S102.2 – 25/50 rated
 - ▶ UL 94 Flammability Classification (#E300774)
 - ▶ NFPA 90 A - 90 B

MADE IN THE
USA